



SUBSTRATE: PROCESSED BOARD – CHIPBOARD, MDF BOARDS

DESCRIPTION: UNIVERSAL CONTRACTORS ACRYLIC A NEW ECONOMICAL WATER BASED COATING INTERIOR / EXTERIOR

SYSTEM TABLE

TECHNICAL DATA	1 ST COAT	2 ND COAT	3 RD COAT	4 TH COAT
PRODUCT NAME	UNIVERSAL SOLVENT BASED PLASTER PRIMER	UNIVERSAL CONTRACTORS ACRYLIC	UNIVERSAL CONTRACTORS ACRYLIC	
PRODUCT CODE	PR100	PVA00	PVA00	
LIFE EXPECTANCY	3 YEARS	3 YEARS	3 YEARS	
WB/SB	SOLVENT BASED	WATER BASED	WATER BASED	
SMOOTH/TEXTURE	SMOOTH	SMOOTH	SMOOTH	
COLOUR	WHITE	WHITE	WHITE	
VOLUME SOLIDS %	40	34	34	
FILM BUILD	WFT 75 - 100µm DFT 30 – 40 µm	WFT 74 - 103 µm DFT 25 - 35 µm	WFT 74 - 103µm DFT 25 - 35µm	
SPREADING RATE DFT	TSR 11,4m ² /lit @35µm PSR 6,5m ² /lit@35µm	TSR 11,3m ² /lit @30µm PSR 6,2m ² /lit@30µm	TSR 11,3m ² /lit@30µm PSR 6,2 ² /lit@30µm	
DRYING TIMES @23°C	16 HOURS	4-6 HOURS	4 -6 HOURS	
VOC % GRAMS PER LITRE	41,79 531,69	0,31 4,48	0,31 4,48	
CLEANING	MINERAL TURPS	WATER	WATER	



SURFACE PREPARATION METHOD STATEMENT

Ensure that surfaces are dry, sound and clean.

Wood Moisture content when measured on Protimeter Moisture Meter must be in the Green Zone which has a value of 16 or below (up to 75% ERH.)

Fill holes and other surface defects with Universal Crack Filler (ACR00) Allow 4 hours to dry, then sand to a smooth finish. Dust off.

APPLICATION METHOD STATEMENT

Apply 1x coat of [UNIVERSAL Solvent Based Plaster Primer](#) at a minimum of 75 µm WFT allow 16 hours to dry at 23°C & 50% RH.

Apply 2 x coats of [UNIVERSAL Contractors Acrylic](#) at a minimum of 74 µm WFT per coat, allowing 2-4 hours drying between coats at 23°C and 50% RH

FOOT NOTES:

TSR	= Theoretical Spread Rate
PSR	= Practical Spread Rate
VOC	= Volatile Organic Compound
WFT	= Wet Film Thickness
DFT	= Dry Film Thickness
ERH	= Equilibrium Relative Humidity
RH	= Relative Humidity