



UNIVERSAL ALLWOOD PRODUCT CODE: ALW00

TECHNICAL DATA SHEET

APRIL 2024 REVISION 1

PRODUCT DESCRIPTION

Universal Allwood is manufactured using low viscosity oils blended with selected linseed oils and UV absorbers.

PRODUCT FEATURES AND BENEFITS

For exterior sanded wooden window frames, wooden doors and frames, skirting's and garden furniture

Life expectancy of at least 1-2 years

Highly durable

UV resistant

PRODUCT INFORMATION

Colour	Clear
Surface Appearance	Gloss or Matt finish
Resin Base	Alkyd Based
Solids Content	By volume: Approx. 41%
VOC Content	Very High VOC content more than 50%
Spreading Rate	Theoretical Spreading Rate: 13,7m²/litre @ 30 µm DFT Practical Spreading Rate: 7,5m²/litre @ 30 µm DFT Our spreading rate is calculated per coat on a smooth surface. This is a guide only. The rate will vary depending on the porosity and profile of the substrate. Tools used and application technique/ method will also have an impact on spreading rate.
Recommend WFT & DFT	61 – 85 µm WFT depending on the surface, porosity, profile and application method 25 – 35 µm DFT depending on the surface, porosity, profile and application Method
Pack Sizes	Available in 1ℓ & 5ℓ
Storage and Packaging	Store away from direct sun, heat and severe cold Ensure the container is tightly sealed before storing. If not sealed properly and exposed to extreme temperatures, it will lead to defects such as product fouling, skinning, crystallizing and will have hard settlement.



APPLICATION DETAILS

Mixing	Stir thoroughly with a flat paddle until homogeneous
Application Conditions	Surface Temperatures at 23°C Relative Humidity <50%
Recoating Time	18-24 hours to dry before over coating
Application Methods	Brush or Roller
Thinner	Is ready for use, do not thin.
Cleaning of equipment	Universal Mineral Turpentine

SURFACE PREPARATION

NEW SURFACES WOOD

The substrates must be clean, dry and sound and free of any contaminants

Machine Sand or hand sand in direction of grain using 100 – 150 grit paper

Dust off

Apply 3 coats Universal Allwood allowing 18-24 hours to dry between coats

PREVIOUSLY COATED SURFACES WOOD

The substrates must be clean, dry and sound and free of any contaminants

Remove all loose and flaking paint and sand existing coating

Machine Sand or hand sand in direction of grain using 100 – 150 grit paper

Dust off

Apply 3 coats Universal Allwood allowing 18-24 hours to dry between coats



CAUTIONS

It is preferable to buy all the paint you need at one time and in the largest possible pack size for convenience and to reduce the chances of slight colour variations between batches

The correct surface preparation is critical to ensure optimum performance of the paint system

Avoid painting during inclement weather

Don't wash, or wet, painted surfaces for 7 days after painting

High humidity will retard the drying and curing

Procedure to change a system from solvent to water based OR water to solvent based.

1. Sand surface slightly with fine sandpaper to break down the existing surface to a matt finish.
2. Dust off any loose dirt contaminants.
3. Clean the surface with soap solution.
4. Rinse well with clean water.
5. Allow the surface to dry completely.
6. Apply one coat of universal undercoat.
7. Apply two coats of the selected top coat (solvent or water based).

SAFETY PRECAUTIONS

For detailed safety information please refer to Material Safety Data Sheet

Keep out of reach of children, flames and sparks

This product is lead free, contains very high levels of VOC

Only use in well ventilated areas and do not eat, drink or smoke whilst using this product

Empty containers are suitable for recycling. But caution must be exercised in the disposal of used containers

DISCLAIMER

Universal Paints cannot be held liable if the product fails due to improper surface preparation or application